

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Hurford Wholesale
400 Stapylton-Jacobs Well Road
Stapylton QLD 4207

Test Number : 23-000779
Issue Date : 17/03/2023
Print Date : 17/03/2023

Sample Description Clients Ref : "Genuine Oak 14mm"
Engineered timber flooring
Colour : Oak
End Use : Flooring
Nominal Composition : Oak lamelia on ply substrate
Nominal Mass per Unit Area/Density : 620g/m²
Nominal Thickness : 14mm



291256

63212

Page 1 of 3

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



Chris Campbell

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Hurford Wholesale
400 Stapylton-Jacobs Well Road
Stapylton QLD 4207

Test Number : 23-000779
Issue Date : 17/03/2023
Print Date : 17/03/2023

AS ISO 9239.1-2003

Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using a Radiant Heat Source

Date of Sample Arrival 24-02-2023

Date Tested 17-03-2023

CHF Value	1	2	3	Mean
Length	3.4	4.2	3.9	3.8 kW/m ²
Width	4.3	-	-	- kW/m ²

HF-30 Value	1	2	3	Mean
Length	4.5	4.5	4.0	4.3 kW/m ²
Width	4.9	-	-	- kW/m ²

Smoke Value	1	2	3	Mean
Length	53	1	39	31 % .min
Width	68	-	-	- % .min

Observation
Blistering Yes

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2010 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

Results in accordance with section 8.4 have not been included in the report. They are available upon request.

Each specimen was clamped to a substrate of 6mm thick fibre reinforced cement board prior to testing.

291256

63212

Page 2 of 3

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



Chris Campbell

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Hurford Wholesale
400 Stapylton-Jacobs Well Road
Stapylton QLD 4207

Test Number : 23-000779
Issue Date : 17/03/2023
Print Date : 17/03/2023

291256

63212

Page 3 of 3

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



0204/11/06

A handwritten signature in black ink, appearing to be 'Chris Campbell'.

Chris Campbell

APPROVED SIGNATORY

A handwritten signature in black ink, appearing to be 'Michael A. Jackson'.

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR